

JUN. 30. 2005 2:36PM

RECEIVED
CENTRAL FAX CENTER
JUN 30 2005

NO. 4124 P. 1/2

PTO/SB/97 (09-04)

Approved for use through 07/31/2006. OMB 0651-0031

U.S. Patent and Trademark Office; U.S. DEPARTMENT OF COMMERCE

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it contains a valid OMB control number.

Certificate of Transmission under 37 CFR 1.8

USPTO Fax No.: (703) 872-9306

I hereby certify that this correspondence is being facsimile transmitted to the United States Patent and Trademark Office

on June 30, 2005
Date

M. Kay Lilly
Signature

M. Kay Lilly

Typed or printed name of person signing Certificate

Registration Number, if applicable

Telephone Number

Note: Each paper must have its own certificate of transmission, or this certificate must identify each submitted paper.

10/775,848
EL0542USNA

— Part 2

SUPPLEMENTAL INFORMATION DISCLOSURE STATEMENT
PTO/SB/08A FORM
COPY OF DE 198 46 098 A1 AND (TRANSLATION)
RETURN POSTAL RECEIPT CARD
CERTIFICATE OF TRANSMISSION

Last page being sent.

Page 1 of 1

This collection of information is required by 37 CFR 1.8. The information is required to obtain or retain a benefit by the public which is to file (and by the USPTO to process) an application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.11 and 1.14. This collection is estimated to take 1.8 minutes to complete, including gathering, preparing, and submitting the completed application form to the USPTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, P.O. Box 1450, Alexandria, VA 22313-1450. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Commissioner for Patents, P.O. Box 1450, Alexandria, VA 22313-1450.

2-pyrrolidone, n-methyl-2-pyrrolidone, n-ethyl-pyrrolidone, n-vinylpyrrolidone, 1,3-dimethyl-imidazolidone, dimethylacetamide as well as dimethylformamide or their mixtures.

16. Preparations in accordance with claims 1 to 15 containing

- a) 0.05 to 80 weight %, preferably 0.1 to 30 weight %, particularly preferably 0.5 to 20 weight % at least of one oxide of element a), related to the preparation,
- b) 0.1 to 200 weight %, preferably 0.5 to 100 weight % and especially 1 to 20 weight % dispersing agent of element b), related to the adopted oxide amount of a),
- c) 10 to 98 weight %, in particular 20 to 98 weight %, solvents of element c) related to the preparation.

17. Technique for the application of pressure ink from ternary oxides of element a) with a median particle size of 1 to 100 nm with the ink jet technique to structured areas on a glass plate or another transparent high-melting polymeric mount.

18. Technique according to claim 17, whereby after the deposition of the pressure ink on a surface, a subsequent sintering of the imprinted substrate in a reducing atmosphere (preferably an argon/hydrogen gas mixture) at temperatures from 150 to 600°C, producing transparent electrically conductive layers

19. Technique according to claim 17, whereby after deposition of the pressure ink on a polymeric mount, the temperature required for sintering the particles is provided by a suitable laser or by a hot air stream.

Language Services Unit

Phoenix Translations

June 27, 2005

MACHINE ASSISTED TRANSLATION

6-7005